



CERAMICHE  
•CAESAR•  
LA CULTURA DELLA MATERIA

Classificazione secondo EN ISO 14411 ISO 13006 annesso G gruppo B1A con E ≤ 0,5 % UGL - Classification in accordance with EN ISO 14411 ISO 13006 annex G standards B1A with E ≤ 0,5% UGL Classification selon EN ISO 14411 ISO 13006 annexe G groupe B1A avec E ≤ 0,5% UGL - Klassifizierung gemäß EN ISO 14411 ISO 13006 anlage G Gruppe B1A mit E ≤ 0,5% UGL - Классификация в соответствии с EN ISO 14411 ISO 13006, приложение G, стандарт B1A, где E ≤ 0,5% UGL

	<b>CARATTERISTICA TECNICA - TECHNICAL CHARACTERISTIC</b> CARACTÉRISTIQUE TECHNIQUE - TECHNISCHE DATEN	<b>NORMA - NORMS</b> NORME - NORM NORMA	<b>VALORE * MEDIO "CAESAR"</b> AVERAGE "CAESAR" VALUE * - VALEUR * MOYEN "CAESAR" "CAESAR" DURCHSCHNITTSWERT * СРЕДНЕЕ ЗНАЧЕНИЕ "CAESAR"**	<b>EXTRA20</b> gardening&outdoor SOLUTIONS	<b>VALORE * MEDIO "CAESAR"</b> AVERAGE "CAESAR" VALUE
	Dimensione - Size Dimension - Abmessungen - Размер	ISO 10545-2	Conforme - In accordance Conforme - Erfüllt - Соответствует	Conforme - In accordance Conforme - Erfüllt - Соответствует	
	Absorimento d'acqua* - Water absorption* Absorption d'eau* - Waseraufnahme* - % Поглощението на вода*	ISO 10545-3	0,05%	0,05%	
	Water absorption*  Resistenza alla flessione* - Bending strength* Résistance à la flexion* - Biegezugfestigkeit* - Упругость*	◆ ASTM C373-88 (2006)	In accordance	In accordance	
	Sforzo di rottura (S) - Breaking strength Charge de rupture - Bruchlast - Esfuerzo de ruptura	ISO 10545-4	Conforme - In accordance Conforme - Erfüllt - Соответствует	Non applicable a piastrelle con una forza di rottura Not applicable to tiles with a breaking strength N'est pas applicable aux carreaux avec une charge de rupture Nicht anwendbar bei Fliesen mit einer Bruchlast Не применим в отношении плиток с прочностями на разрыв	≥ 3000 N ≥ 3000 N ≥ 3000 N ≥ 3000 N ≥ 3000 N
	Resistenza all'abrasione profonda* - Deep scratch resistance* Résistance à l'abrasion profonde* - Widerstand gegen Tiefenverschleiß* Устойчивость глубокому износу**	ISO 10545-6	≤ 145 mm³	≤ 145 mm³	
	Coefficiente di dilatazione termica lineare* - Thermal linear expansion coefficient* - Coefficient de dilatation thermique linéaire - Коэффициент линейного теплового расширения**	ISO 10545-8	= 6,5 (10⁻⁶ °C⁻¹)	= 6,5 (10⁻⁶ °C⁻¹)	
	Resistenza agli sbalzi termici* - Thermal shock resistance* Résistance aux écarts de température* - Temperaturwechsel Beständigkeit* Устойчивость к тепловому перенападу**	ISO 10545-9	Resistente - Resistant Résistante - Beständig - Стойкий	Resistente - Resistant Résistante - Beständig - Стойкий	
	Dilatazione all'umidità* - Expansion in humidity* Dilatation à l'humidité* - Feuchtigkeitsausdehnung* Расширение в условиях влажности**	ISO 10545-10	≤ 0,1 (mm/m)	≤ 0,1 (mm/m)	
	Resistenza al gelo* - Frost resistance* Résistance au gel* - Frostbeständigkeit* - Морозустойчивость*	ISO 10545-12	Resistente - Resistant Résistante - Beständig - Стойкий	Resistente - Resistant Résistante - Beständig - Стойкий	
	Resistenza all'attacco chimico* - Resistance to chemical attack* Résistance à l'attaque chimique* - Beständigkeit gegen Chemikalien* Устойчивость к химическому воздействию**	ISO 10545-13	Resistente - Resistant Résistante - Beständig - Стойкий	Resistente - Resistant Résistante - Beständig - Стойкий	
	Carico statico - Static load Charge statique - Statiche Last Carga estática	EN 12825	-	Centro - Centre - Au centre - Mitte - По центру Centro laterale - Side centre - Au centre latéralement Mitte Seite - По центру грани Diagonale - Diagonal - En diagonale Diagonal - По диагонали	60x60 KN-8,0 KN-5,5 KN-8,0
	Classe di carico di rottura*** Breaking load class*** - Classe de charge de rupture*** Bruchlastklasse*** - Clase de carga de rotura***	EN 1339	-	U11*** T11***	
	Resistenza alle macchie* - Resistance to stains* Résistance aux taches* - Fleckenbeständigkeit* Устойчивость к образованию пятен**	ISO 10545-14	Pulibile - Cleanable Nettoyable - Leicht zu reinigen Чистящийся	Pulibile - Cleanable Nettoyable - Leicht zu reinigen Чистящийся	
	Resistenza allo scivolamento** - Slip resistance** Résistance au glissement** - Rutschhemmende Eigenschaft** Сопротивление скольжению**	DIN 51130-51097	Naturale - Matt Naturel - Natur Матовая	Grip	R11 A+B+C
		ASTM C1028	C.O.F. WET ≥ 0,60	R9 C.O.F. DRY ≥ 0,60	≥ 0,70 ≥ 0,70
			△ DCOF	Conforme - In accordance Conforme - Erfüllt - Соответствует	Conforme - In accordance Conforme - Erfüllt - Соответствует
	Spessore nominale - Nominal Thickness Epaisseur nominale - Nominalstärke Номинальная толщина		10 mm	20 mm	

\* Valori medi riferiti agli ultimi due anni di produzione e relativi alla finitura naturale del prodotto - Average values referred to the last two years of production and related to the matt finish of the product - Valeurs moyennes des deux dernières années de production et relatives à la finition naturelle du produit - Durchschnittswerte, die sich auf die letzten zwei Produktionsjahre beziehen und auf die matte Oberfläche - Средние значения относятся к последним двум годам производства и натуральной отделке поверхности.

\*\* Valori relativi alla finitura naturale del prodotto ed a test effettuati da laboratori esterni accreditati, disponibili in azienda; ci rendiamo disponibili alla verifica dell'eventuale lotto interessato all'acquisto.

As far as values relating to the matt finish of the product and to tests carried out by certified external laboratories whose results are available upon request at Headoffice, we are willing to check the lot you are interested in purchasing.

Valuers se référant à la finition naturelle du produit selon des tests effectués par des laboratoires extérieurs accrédités et à la disposition de toute personne intéressée auprès de nos bureaux; nous sommes disponibles pour le contrôle de l'éventuel lot concerné par l'achat. - Werte bezogen auf das natürliche Produktfinish und in anerkannten externen Labors geprüft, im Unternehmen erhältlich; für eventuelle Prüfungen der zu erwerbenden Warenposten stehen wir gern zur Verfügung. - Эчнения, касающиеся натуральных характеристик изделий и тестов, выполненных внешними авторизованными лабораториями, имеются компаниями. Мы готовы выполнить проверку партии товара, которую намеревается приобрести.

\*\*\* Dato riferito al formato 60x60 cm - Detail referred to the 60x60 cm size. - Donnée se rapportant au format 60x60 cm. - Auf das Format 60x60 cm bezogen. - Эчнения, касающиеся натуральных характеристик изделий и тестов.

● Per prodotti chimici di uso domestico e additivi per piscina - For domestic chemicals and swimming pool additives - Pour produits chimiques à usage domestique et additifs pour piscines - Für chemische Produkte für den Haushalt und Schwimmbecken - Для бытовых химикатов и добавок для бассейнов.

▲ Valore minimo richiesto ANSI A137.1 - 2012 > 0,42 - Minimum Value Required ANSI A137.1 - 2012 > 0,42 - Valeur Minimum Demandée ANSI A137.1 - 2012 > 0,42 - Erforderlicher Mindestwert ANSI A137.1 - 2012 > 0,42 - Минимальное требуемое значение по ANSI A137.1-2012 >0,42

◆ Valore richiesto ANSI A137.1-2012 WA≤ 0,5% - Value Required ANSI A137.1-2012 WA≤ 0,5% - Valeur Demandée ANSI A137.1-2012 WA≤ 0,5%- Erforderlicher Wert ANSI A137.1-2012 WA≤ 0,5% - Требуемое значение ANSI A137.1 2012 WA≤ 0,5%